



SINCE
1950

MOKRUTEX PES K

Calendered nonwoven geotextile



STANDARD
100



PG035 217573
OETI




STANDARD
100



PG035 217550
OETI



- Characteristic:** Nonwoven textile mechanically bonded by needle punching and thermally by calender
- Material content:** Recycled polyester
- Color:** Multicolor and monochromatic
- Weight:** 200 - 500 g/m²
- Maximum width:** 4 m
- Function:**



SEPARATION



FILTRATION



PROTECTION




DRAINAGE

Use:




EN 13249:2016




EN 13250:2016




EN 13251:2016




EN 13252:2016




EN 13253:2016




EN 13254:2016



EN 13255:2016



EN 13256:2016



EN 13257:2016



EN 13265:2016

Material specification sheet

Date: 11.12. 2023

Quality Management System ISO 9001, ISO 14001, ISO 45001 a ISO 50001

SINCE
1950

TRADITIONAL QUALITY NONWOVENS

Material specification sheet

Date: 11.12. 2023

MOKRUTEX PES K

Calendered nonwoven geotextile

MOKRUTEX PES K			200	300	500
PHYSICAL PROPERTIES					
Weight [$\pm 10\%$] / EN ISO 9864		g/m ²	200	300	500
Thickness 2 kPa [$\pm 15\%$] / EN ISO 9863-1		mm	1,6	1,8	2,6
MECHANICAL PROPERTIES					
Tensile strenght / EN ISO 10319	MD	kN/m	3,5-0,5	6,5-1	10-2
	CMD		3,5-0,5	6,5-1	10-2
Elongation [$\pm 20\%$] / EN ISO 10319	MD	%	60	60	65
	CMD		80	80	70
Resistance to static puncture - CBR test / EN ISO 12236		kN	0,7-0,1	1-0,1	2-0,2
Dynamic perforation test (cone drop test) / EN ISO 13433		mm	30+3	24+1,5	15+1
Pyramid puncture resistance [-20] / EN ISO 14574		N	169 \pm 13,5	230 \pm 18,3	355 \pm 27,9
HYDRAULIC PROPERTIES					
Characteristic opening size O90 / EN ISO 12956 [$\pm 15\%$]		μ m	84 \pm 16,8	70 \pm 14	65 \pm 13
Water permeability normal to the plane VIH50 / EN ISO 11058		l/m ² .s	64-9,6	34,9-5,2	20,2-3
Water permeability in the plane (longitudinal direction) gradient 0,1 [$\pm 15\%$] EN ISO 12958	20 kPa	l/m.s	2,66*10 ⁻⁴	2,9*10 ⁻⁴	3,51*10 ⁻⁴
	100 kPa		-3,99*10 ⁻⁵	-4,35*10 ⁻⁵	-5,27*10 ⁻⁵
	200 kPa		5,85*10 ⁻⁵	7*10 ⁻⁵	1,29*10 ⁻⁴
			-8,78*10 ⁻⁶	-1,05*10 ⁻⁵	-1,94*10 ⁻⁵
Water permeability in the plane (longitudinal direction) gradient 1 [$\pm 15\%$] EN ISO 12958	20 kPa	l/m.s	2,69*10 ⁻⁵	3,1*10 ⁻⁵	6,60*10 ⁻⁵
	100 kPa		-4,04*10 ⁻⁶	-4,65*10 ⁻⁶	-9,9*10 ⁻⁶
	200 kPa		2,76*10 ⁻³	3,1*10 ⁻³	3,62*10 ⁻³
			-4,14*10 ⁻⁴	-4,65*10 ⁻⁴	-5,43*10 ⁻⁴
			6,04*10 ⁻⁴	8*10 ⁻⁴	1,28*10 ⁻³
			-9,06*10 ⁻⁵	-1,2*10 ⁻⁴	-1,92*10 ⁻⁴
			3,05*10 ⁻⁴	3,5*10 ⁻⁴	6,85*10 ⁻⁴
			-4,58*10 ⁻⁵	-5,25*10 ⁻⁵	-1,03*10 ⁻⁴
ENDURANCE					
Resistance to hydrolysis EN 12447	/	min. 50	>75	>75	>75
Protection efficiency [$\pm 10\%$] / EN 13719	300 kPa	%	2,06 \pm 0,41	1,85 \pm 0,46	1,47 \pm 0,37
Resistance to weathering 12224		/ EN ISO	Must be covered within 1 month after being placed		
Life expectancy			Min. 5 years in natural soils with 4<pH<9 with soil temperature < 25 °C.		
FUNCTION					
Separation		S	X	X	X
Filtration		F	X	X	X
Drainage		D	X	X	X
Reinforcement		R			
Protection		P	X	X	X
CHARACTERISTICS					
Description	Nonwoven textile mechanically bonded by needle punching				
Material content	Recycled polyester				
Color	Multicolor and monochromatic				
DIMENSION, PACKAGING AND STORAGE					
Roll width		m	4	4	4
Roll length		m	50	50	25
Packaging	Rolls are wound on a paper tube, wrapped in PE foil and palletized.				
Storage	In covered, clean and dry spaces				

The above technical parameters are average values and serve for general information. The manufacturer reserves the right to change it.