

DHONAL

DECLARATION OF CHARACTERISTICS Number: MK HQ PP K 250 / 2020

Polypropylene needlepunched calendered nonwoven geotextile Mokrutex HQ PP K

MOKRUTEX HQ PP K 250

Needle punched nonwoven geotextile used for building of motorways, railways, land buildings, bulding of dams, canals
and drainage systems with separation and filtration, reinforcement, protection drainage function (S, F, R, P, D)

RETEX a.s. U nádraží 894 672 01 Moravský Krumlov, CZ e: geo@retex.cz · i: www.retex.cz

1.

3.

4.

System for adjudicatation and verification of building products : **2+**

Textilní zkušební ústav s.p. - notified subjekt 1021 executed initial adjudication of production management system in accordance with system 2 +, performes regular witness on the production system and issued certificate No. 1021-CPR - 100 - 1/17

Character		Norm	Unit	Mean value	Tolerance	Harmonic technic norm
Square weight		EN ISO 9864	g/m ²	250	± 10 %	EN 13249:2016
Strength	MD	EN ISO 10319	kN/m	20	- 1	EN 13250:2016 EN 13251:2016 EN 13252:2016 EN 13253:2016 EN 13254:2016
	CMD		kN/m	20	- 1	
Tensibility	MD	EN ISO 10319	%	65	± 15	
	CMD		%	75	± 15	
Thickness 2 kPa		EN ISO 9863-1	mm	1,4	± 15 %	EN 13255:2016 EN 13256:2016 EN 13257:2016 EN 13265:2016
Static puncture - CBR test		EN ISO 12236	kN	3,2	- 0.1	
Dynamic puncture - cone drop test		EN ISO 13433	mm	13	+ 2	
Determination of the pyramid puncture resistance		EN 14574	N	228	- 20	
Characteristic opening size 0 ₉₀		EN ISO 12956	μm	99	± 15	
Determination of water permeability characteristics normal to the plane VI _{H50}		EN ISO 11058	I/m ² . s	17,3	-2.5	
Determination of water flow capacity in their plane - gradient 0.1 / longitudinal direction	20 kPa	EN ISO 12958	I/m². s	1.58 x 10 ⁻⁴	± 15 %	
	100 kPa			7.88 x 10 ⁻⁵		
	200 kPa			6.36 x 10 ⁻⁵		
Determination of water flow capacity in their plane - gradient 0.1 / longitudinal direction	20 kPa	EN ISO 12958	I/m². s	1.57 x 10 ⁻³		
	100 kPa			7.73 x 10 ⁻⁴		
	200 kPa			6.72 x 10 ⁻⁴		
Resistance to weather conditions		EN ISO 12224	Must be covered within 1 month after being placed.			
Determining the resistance to oxidation	MD	EN ISO 13438	90.90 %		<u>-</u>	
	CMD		76.40 %			
Determination of the long term protection efficiency 300 kPa		EN 13719	%	1,59	± 1.6	
Dangerous substances			Less than EU states requirements		Valid national regulations EU states	

It is assumed that nonwoven will be durable for a minimum of 100 years in natural soils with 4<pH<9 with soil temperature < 25 °C.

8. ...

Characteristics of the above mentioned product are in accordance with complex of declared characteristics.

This declation of characteristics is in accordance with EU directive No. 305/2011 issued in responsibility of producer mentioned above.

Signed by the manufacturer and his name: In Moravský Krumlov: 05.03.2021

Ing. Robert Šimek, Ph.D.

Chairman of the executive board